## 222 Product Line



UNS N06022 Alloy

Material Type:	Nickel-Chromium-Molybdenum Alloy (UNS Designation N06022) <sup>1</sup>
Dimensions:	ASTM Tube Sizes: • 1/4" to 3/4" (6.35mm to 19.05mm)
Reference Documents:	ASTM: B 622
Tube Lengths:	• 18.5-feet to 20.083-feet (5.64-meters to 6.121-meters)
Manufacturing Method & Mechanical Properties:	Seamless Tensile Strength 110 ksi (758.4 MPa) minimum.
Tolerances:	Outside Diameter: ±.005" Wall Thickness: ±12.5%
I.D. Surface Roughness:	• 20 micro-inches (.51 micro-meters) Ra max.
Weld Ends:	Square ends suitable for orbital welding
Testing & Inspection:	<ul> <li>Visual inspection</li> <li>Surface roughness measurement</li> <li>Helium-leak test &amp; Dimensional inspection</li> </ul>
Marking & Traceability:	Each component is traceable to its producing mill and heat by an identification number etched within 24" (610mm) of one end.
Labeling:	Each component's bag is affixed with a label identifying the component's part number, date and Valex lot number.
Documentation:	<ul> <li>A Quality Inspection Certificate is furnished with each shipment.</li> <li>The report contains the following information: <ul> <li>a. Material composition &amp; applicable specification designation</li> <li>b. Nominal outside diameter size</li> <li>c. Chemical composition</li> <li>d. Statement of quality assurance testing</li> <li>e. Inspection Certificate type 3.1 per EN 10204:2004</li> <li>f. Lot &amp; heat identification for traceability</li> </ul> </li> </ul>
Packaging:	All tube and fittings are purged with UHP nitrogen, capped, bagged and packaged for shipment in such a manner which prevents damage to product and primary-product packaging.

<sup>&</sup>lt;sup>1</sup> Haynes Hastelloy® C-22® is available upon request. Hastelloy and C-22 are registered trademarks of Haynes International Inc. SP-9207 O Valex | USA, South Korea, China